

PRIMA INFINITO & VOLARE & UNIQ

SCHEDA TECNICA Revisione: 18/10/2022

Prodotto: Prima Infinito & Volare & Uniq

Categoria: Fondi Azienda: Loggia

General Characteristics

Specific primer based on special acrylic copolymers, pigments and selected fillers. Excellent coverage and yield.

Application

Used as a base for the products Infinito and Volare.

Preparation



Check that 4-5 hours have passed since the application of Fissacril and that the surface is perfectly clean. Apply the product as described below.





<u>Application Methods</u>



Brush and roller: Dilute 20-25% with water for brush application and 15-20% for roller application.

| Application temperature: | +5 ÷ +35 | °C |
|-----------------------------------|----------|-------------|
| Relative humidity of application: | < 85% | |
| Recommended thickness: | 35 ÷ 50 | μm per coat |
| Dust dry: | 0,5 | h |
| Repaintable after: | 5 ÷ 6 | h |
| Deep dry: | 24 | h |
| Tool cleaning: | water | |

Painting:



The product can be colored with the tinting system of the L'ANGELO 4OX and MAXXI lines.

It is advisable to mix different manufacturing batches of the same color with each other to avoid possible differences in shades during application.

| Specific weight: | 1,2 ÷ 1,3 | Kg/I |
|--------------------|------------------|---------------|
| Viscosity: | 8000 - 10000 | cPs |
| pH: | 7 - 8 | |
| Solid in weight: | 58% | |
| Theoretical yield: | 8 - 10 | mq/l per coat |
| Color | Color folder 4OX | |
| Aspect | Mat | |
| Packaging: | 5 -15 | L |

Storage:





The unopened product, stored intact in a dry and cool place, has a shelf life of not less than 24 months. After use, carefully close the package and store it upside down.





Minimum storage temperature: + 5 ° C.

Maximum storage temperature: + 30 ° C.

Safety Precautions:

For all information relating to the handling of the product, as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.I. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.